



MATERIAL TESTING LABORATORY
MILITARY ENGINEER SERVICES (MES)
TEST RESULT FOR FINENESS MODULUS(F.M.) OF SAND.

Page No: 163

Copy no : 01

Job No : 63/2025-2026 (Sand).
Name of Clint : GE (Army) Barishal.
Ref Itr no : CEA/123 of 2025-2026/06/E-6 Dt.24 Dec'2025.
Project Name : Construction of RCC Post for Island-02, 03 & 04.
Sample Specimen : Sylhet Sand.
Dt of sample collection : 28 Dec'2025
Test Standard : ASTM/BS

Sieve Size	Wt of Material Retainned(gms)	Percentage Matarial Retained(Round)	Cumulative % Retained	%Finer	Remarks
# 4	0	0.00	0.00		
# 8	14.9	3.73	3.73		
#16	70.06	17.52	21.24		
# 30	177.44	44.36	65.60		
# 50	116.38	29.10	94.70		FM= 2.85
#100	19.63	4.91	99.60		
# 200	1.27	0.32	..		
#Pan	0.26	0.07	...		
			$\Sigma= 284.86$		

Cautions :

- 1 Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the sample to be tested.
- 2 It is recommended that samples are sent in a sealed cover/packet/container under signature of the competent authority
- 3 In oder to be avoid fraudulent fabrication of the test result ,it is recommended that test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1

Laboratory Technician

Test Performed By

Vetted By

Permissible Value:

1. For Sylhet/Domar sand minimum FM will be = 2.50
2. For Local sand minimum FM will be = 1.5
3. For Vitty sand minimum FM will be = 0.80