



**MATERIAL TESTING LABORATORY**  
**MILITARY ENGINEER SERVICES(MES)**

Page No: 934

Copy no : 02

**TEST RESULT FOR COMPRESSIVE STRENGTH OF CONCRETE CYLINDER/CUBE**

Job No : 638/2024-2025 (Con).  
Name of Client : GE (Army) Central, Dhaka.  
Ref ltr no : 6000/Mosque/22/E-6 Dt.25 May'2025.  
Name of the project : Construction of Islamic center & Library.  
Status of sample : 1st floor slab.  
Dt of sample collection: 25 May'2025  
Test Standard : ASTM/BS

Sample Specimen: Ht 200mm(8") Dia 100 mm(4")  
Type of Aggregate : Stone  
Brand & Type of Cement : Seven rings Opc.  
Proportion of Mixture : 1:1.25:2.5  
Desired Design Strength : 4500 Psi.

Ser no.	Date of casting and (Age in days)	Date of Test	Specimen Area Sq inch	Maximum Load (Lbs)	Crushing Strength (Psi)	Average Crushing Strength (Psi)	Remarks
1	19 May'2025 (28 days)	16 Jun'2025	12.17	43627.38	3585	Average of Sample 2 & 3  2828	Combined Failure
2			12.17	35050.73	2880		
3			12.17	33774.92	2775		

**Cautions :**

- 1 Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the sample to be tested.
- 2 It is recommended that samples are sent in a sealed cover/packet/container under signature of the competent authority
- 3 In order to avoid fraudulent fabrication of the test result, it is recommended that test reports should be collected by duly authorized person and not by the contractor/supplier.

**Observation on Specimen(if any):**

- 1 As the strength is below the desired design strength, so nec. measures to be taken as per particular specifications of contract.

Laboratory Technician

Test Performed By

Vetted By

Note:[1 Mpa=145 psi, 1kg/cm<sup>2</sup>=14.223 Psi]

