



**MATERIAL TESTING LABORATORY**  
**MILITARY ENGINEER SERVICES (MES)**  
**TEST RESULT FOR FINENESS MODULUS(F.M.) OF SAND.**

Page No: 150

Copy no : 01

Job No : 64/2025-2026 (Sand).  
Name of Clint : GE (Navy) North, Chattogram.  
Ref Itr no : CEN/189 of 2024-2025/13/E-6 Dt.30 Dec'2025  
Project Name : Construction of Multipurpose Complex.  
Sample Specimen : Sylhet Sand.  
Dt of sample collection : 01 Jan'2026  
Test Standard : ASTM/BS

Sieve Size	Wt of Material Retainned(gms)	Percentage Matarial Retained(Round)	Cumulative % Retained	%Finer	Remarks
# 4	9	2.25	2.25		
# 8	24.38	6.10	8.35		
#16	83.86	20.97	29.31		
# 30	204.67	51.17	80.48		
# 50	66.74	16.69	97.16		FM= 3.17
#100	7.41	1.85	99.02		
# 200	0.91	0.23	..		
#Pan	0.42	0.11	...		
			$\Sigma= 316.56$		

Cautions :

- 1 Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the sample to be tested.
- 2 It is recommended that samples are sent in a sealed cover/packet/container under signature of the competent authority
- 3 In oder to be avoid fraudulent fabrication of the test result ,it is recommended that test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1

Laboratory Technician

Test Performed By

Vetted By

Permissible Value:

- 1.For Sylhet/Domar sand minimum FM will be = 2.50
- 2.For Local sand minimum FM will be = 1.5
- 3.For Vitty sand minimum FM will be = 0.80



**MATERIAL TESTING LABORATORY**  
**MILITARY ENGINEER SERVICES (MES)**  
**TEST RESULT FOR FINENESS MODULUS(F.M.) OF SAND.**

Page No: 34

Copy no : 02

Job No : 19/2024-2025(Sand).  
Name of Clint : GE (Navy) North, Chattogram.  
Ref Itr no : CEN/189 of 2024-2025/13/E-6 Dt.30 Dec'2025  
Project Name : Construction of Multipurpose Complex.  
Sample Specimen : Local Sand  
Dt of sample collection : 01 Jan'2026  
Test Standard : ASTM/BS

Sieve Size	Wt of Material Retainned(gms)	Percentage Matarial Retained(Round)	Cumulative % Retained	%Finer	Remarks
# 4	0	0.00	0.00		
# 8	2.91	0.73	0.73		
#16	33.85	8.46	9.19		
# 30	83.4	20.85	30.04		
# 50	158.14	39.54	69.58		FM= 2.05
#100	105.11	26.28	95.85		
# 200	13.87	3.47	..		
#Pan	2.35	0.59	...		
			$\Sigma= 205.39$		

Cautions :

- 1 Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the sample to be tested.
- 2 It is recommended that samples are sent in a sealed cover/packet/container under signature of the competent authority
- 3 In oder to be avoid fraudulent fabrication of the test result ,it is recommended that test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1

Laboratory Technician

Test Performed By

Vetted By

Permissible Value:

- 1.For Sylhet/Domar sand minimum FM will be = 2.50
- 2.For Local sand minimum FM will be = 1.5
- 3.For Vitty sand minimum FM will be = 0.80



**MATERIAL TESTING LABORATORY**  
**MILITARY ENGINEER SERVICES (MES)**  
**TEST RESULT FOR FINENESS MODULUS(F.M.) OF SAND.**

Page No: 32

Copy no : 03

Job No : 07/2024-2025(Sand).  
Name of Clint : GE (Navy) North, Chattogram.  
Ref Itr no : CEN/189 of 2024-2025/13/E-6 Dt.30 Dec'2025  
Project Name : Construction of Multipurpose Complex.  
Sample Specimen : Local Sand (FM = 1.20)  
Dt of sample collection : 01 Jan'2026

Test Standard : ASTM/BS

Sieve Size	Wt of Material Retainned(gms)	Percentage Matarial Retained(Round)	Cumulative % Retained	%Finer	Remarks
# 4	0	0.00	0.00		
# 8	4.22	1.06	1.06		
#16	65.35	16.34	17.39		
# 30	70.42	17.61	35.00		
# 50	95.12	23.78	58.78		FM= 1.97
#100	105.95	26.49	85.27		
# 200	52.93	13.23	..		
#Pan	5.84	1.46	...		
			$\Sigma= 197.49$		

Cautions :

- 1 Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the sample to be tested.
- 2 It is recommended that samples are sent in a sealed cover/packet/container under signature of the competent authority
- 3 In oder to be avoid fraudulent fabrication of the test result ,it is recommended that test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1

Laboratory Technician

Test Performed By

Vetted By

Permissible Value:

- 1.For Sylhet/Domar sand minimum FM will be = 2.50
- 2.For Local sand minimum FM will be = 1.5
- 3.For Vitty sand minimum FM will be = 0.80