



MATERIAL TESTING LABORATORY
MILITARY ENGINEER SERVICE(MES)

Page No : 900

Copy no : 01

TEST RESULT FOR COMPRESSIVE STRENGTH OF CONCRETE CYLINDER/CUBE

Job No : 654/2024-2025 (Con).
Name of Client : GE (Army) Central,Dhaka.
Ref ltr no : EinC/91 of 2022-2023/20/E-6 Dt.28 May' 2025.
Name of the project : Construction of 26 x JCO's Qtr and 52 x OR's Qtr.
Status of sample : 12th floor roof.
Dt of sample collection: 28 May'2025
Test Standard : ASTM/BS

Sample Specimen: Ht 200mm(8") Dia 100 mm(4")
Type of Aggregate : Stone
Brand &Type of Cement : Shah Opc.
Proportion of Mixture : Not Mentioned.
Desired Design Strength : 2600 Psi

Ser no.	Date of casting and (Age in days)	Date of Test	Specimen Area Sq inch	Maximum Load (Lbs)	Crushing Strength (Psi)	Average Crushing Strength (Psi)	Remarks
1	21 May'2025 (07 days)	28 May'2025	12.17	32057.92	2634	Average of Sample 1, 2 & 3 2737	Combined Failure
2			12.17	35073.13	2882		
3			12.17	32794.97	2695		

Cautions :

- 1 Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the sample to be tested.
- 2 It is recommended that samples are sent in a sealed cover/packet/container under signature of the competent authority
- 3 In order to avoid fraudulent fabrication of the test result ,it is recommended that test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1

Laboratory Technician

Test Performed By

Vetted By

Note:[1 Mpa=145 psi, 1kg/cm²=14.223 Psi]