



MATERIAL TESTING LABORATORY
MILITARY ENGINEER SERVICES(MES)

Page No: 166

Copy no : 02

TEST RESULT FOR COMPRESSIVE STRENGTH OF CONCRETE CYLINDER/CUBE

Job No : 74/2025-2026 (Con).
Name of Client : GE (Army) Central, Dhaka.
Ref ltr no : EinC/91 of 2022-2023/141/E-6 Dt.14 Aug'2025.
Name of the project : Construction of 26 x JCO's Qtr and 52 x OR's Qtr.
Status of sample : 13th floor roof .
Dt of sample collection: 14 Aug'2025
Test Standard : ASTM/BS

Sample Specimen: Ht 200mm(8") Dia 100 mm(4")
Type of Aggregate : Stone
Brand & Type of Cement : Shah Opc.
Proportion of Mixture : Not Mentioned
Desired Design Strength : 4000 Psi.

Ser no.	Date of casting and (Age in days)	Date of Test	Specimen Area Sq inch	Maximum Load (Lbs)	Crushing Strength (Psi)	Average Crushing Strength (Psi)	Remarks
1	07 Aug'2025 (28 days)	04 Sep'2025	12.17	56983.64	4682	Average of Sample 1, 2 & 3 4469	Combined Failure
2			12.17	52337.98	4301		
3			12.17	53856.75	4425		

Cautions :

- 1 Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the sample to be tested.
- 2 It is recommended that samples are sent in a sealed cover/packet/container under signature of the competent authority
- 3 In order to avoid fraudulent fabrication of the test result, it is recommended that test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1

Laboratory Technician

Test Performed By

Vetted By

Note:[1 Mpa=145 psi, 1kg/cm2=14.223 Psi]