



**MATERIAL TESTING LABORATORY  
MILITARY ENGINEER SERVICES(MES)**

Page No : 308

Copy no : 01

**TEST RESULT FOR COMPRESSIVE STRENGTH OF CONCRETE CYLINDER/CUBE**

Job No : 79 (D)/2025-2026 (Con).

Name of Client : GE (Air) Tejgaon, Dhaka.

Ref ltr no : CE Air/239 of 2024-2025/31/E-6 Dt.19 Oct' 2025.

Name of the project : Construction of Medical Squadron.

Status of sample : 3rd floor Column.

Dt of sample collection: 21 Oct'2025

Test Standard : ASTM/BS

Sample Specimen: Ht 200mm(8") Dia 100 mm(4")

Type of Aggregate : Stone

Brand & Type of Cement : Crown Opc.

Proportion of Mixture : 1:1.25:2.5

Desired Design Strength : 2800 Psi

Ser no.	Date of casting and (Age in days)	Date of Test	Specimen Area Sq inch	Maximum Load (Lbs)	Crushing Strength (Psi)	Average Crushing Strength (Psi)	Remarks
1	15 Oct'2025 (07 days)	22 Oct'2025	12.17	37552.30	3086	Average of Sample 1, 2 & 3 3079	Combined Failure
2			12.17	35810.18	2942		
3			12.17	39048.73	3209		

Cautions :

- 1 Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the sample to be tested.
- 2 It is recommended that samples are sent in a sealed cover/packet/container under signature of the competent authority
- 3 In order to avoid fraudulent fabrication of the test result ,it is recommended that test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1

Laboratory Technician

Test Performed By

Vetted By

Note:[1 Mpa=145 psi, 1kg/cm<sup>2</sup>=14.223 Psi]