



**MATERIAL TESTING LABORATORY  
MILITARY ENGINEER SERVICES(MES)**

Page No : 80

Copy no : 02

**TEST RESULT FOR COMPRESSIVE STRENGTH OF CONCRETE CYLINDER/CUBE**

Job No : 80(D)/2025-2026 (Con).

Name of Client : GE (Navy) Khulna.

Ref ltr no : EinC/183 of 2022-2023/36/E-6 Dt.22 Oct' 2025.

Name of the project : Construction of 1 x Officers Residence.

Status of sample : 6th floor roof.

Dt of sample collection: 23 Oct'2025

Test Standard : ASTM/BS

Sample Specimen: Ht 200mm(8") Dia 100 mm(4")

Type of Aggregate : Stone

Brand & Type of Cement : Elephant Opc.

Proportion of Mixture : 1:2.894:2.698 (Admixture)

Desired Design Strength : 4000 Psi

Ser no.	Date of casting and (Age in days)	Date of Test	Specimen Area Sq inch	Maximum Load (Lbs)	Crushing Strength (Psi)	Average Crushing Strength (Psi)	Remarks
1	16 Oct'2025 (28 days)	13 Nov'2025	12.17	29400.07	2416	Average of Sample 1, 2 & 3 2531	Combined Failure
2			12.17	30881.57	2538		
3			12.17	32111.82	2639		

Cautions :

- 1 Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the sample to be tested.
- 2 It is recommended that samples are sent in a sealed cover/packet/container under signature of the competent authority
- 3 In order to avoid fraudulent fabrication of the test result ,it is recommended that test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

- 1 As the strength is below the desired design strength, so nec. measures to be taken as per particular specifications of contract.

Laboratory Technician

Test Performed By

Vetted By

Note:[1 Mpa=145 psi, 1kg/cm<sup>2</sup>=14.223 Psi]