



MATERIAL TESTING LABORATORY
MILITARY ENGINEER SERVICES (MES)
TEST RESULT FOR FINENESS MODULUS(F.M.) OF SAND.

Page No: 174

Copy no : 01

Job No : 97/2024-2025(Sand).
Name of Clint : AGE (Air) PKP.
Ref Itr no : EinC/444 of 2022-2023/40/E-6 Dt.22 May'2025
Project Name : Construction of Boundary wall.
Sample Specimen : Sylhet sand
Dt of sample collection : 28 May'2025
Test Standard : ASTM/BS

Sieve Size	Wt of Material Retained(gms)	Percentage Material Retained(Round)	Cumulative % Retained	%Finer	Remarks
# 4	0	0.00	0.00		
# 8	22.99	5.75	5.75		
#16	145.55	36.39	42.14		
# 30	162.98	40.75	82.88		
# 50	60	15.00	97.88		FM= 3.29
#100	8.44	2.11	99.99		
# 200	0.02	0.01			
#Pan	0.18	0.05	...		
			Σ= 328.63		

Cautions :

- 1 Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the sample to be tested.
- 2 It is recommended that samples are sent in a sealed cover/packet/container under signature of the competent authority
- 3 In order to avoid fraudulent fabrication of the test result, it is recommended that test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1

Laboratory Technician

Test Performed By

Vetted By

Permissible Value:

- 1.For Sylhet/Domar sand minimum FM will be = 2.50
- 2.For Local sand minimum FM will be = 1.5
- 3.For Vitty sand minimum FM will be = 0.80